

Fluorescent materials

Patent number: DE19500634
Publication date: 1996-08-29
Inventor: POPALL MICHAEL DR RER NAT [DE]; NEUMANN GERT DR RER NAT [DE]; SCHMIDT HOLGER [DE]; SPANHEL LUBOMIR DR RER NAT [DE]
Applicant: FRAUNHOFER GES FORSCHUNG [DE]
Classification:
- **international:** C09K11/02; C09K11/77; C08G77/24; C07F7/02; C07F9/547; C07F9/50; C08G77/04; C08G77/14; C08G77/28; C08G77/26; C08G77/20; G02F1/35; C08G79/00; C09D5/22; C07F19/00; C07F5/00; C08L83/02; C08G77/12
- **european:** C09K11/06
Application number: DE19951000634 19950111
Priority number(s): DE19951000634 19950111

Also published as:

EP0721976 (A2)
EP0721976 (A3)
EP0721976 (B1)

Abstract not available for DE19500634

Abstract of corresponding document: **EP0721976**

Fluorescent materials (I) have a matrix based on silicic acid (hetero)polycondensate (II) contg. Er³⁺ ions and opt. other additives: in which (a) (II) is a hydrolytic (pre)condensate of cpd(s). of Si and opt. B, Al, Ge, P, As, Sb, Sn, Pb, transition metal(s), lanthanide(s) and/or actinide(s) undergoing hydrolytic condensn. and/or precondensates obt'd. from these cpds. by the action of water or humidity, opt. in the presence of a catalyst and/or solvent; (b) 5-100 mole % (pre)condensed cpds. are based on monomers derived from silanes of formula SiRaXb (III); (c) the Er³⁺ ions are fixed to nanoparticles and/or complexed with organic cpd(s). having at least one available electron pair donor gp.; (d) the nanoparticles have dia. NOT GREATER 20 nm.; (e) (I) contains 10-40 vol.% nanoparticles; and (f) (I) contains 1-50 wt.% Er³⁺ ions, R = an alk(en)yl, (alkyl)aryl or arylalkyl gp., which may have -O-, -S- or -NH- in the chain and/or contain spiro, oxiran, cyclic anhydride or NCO gps., X = H, halogen, OH, alkoxy, acyloxy, alkylcarbonyl, alkoxy carbonyl or NR'², R' = H, alkyl or aryl, a, b = 1, 2 or 3 with (a+b) = 4. Also claimed is a method of producing the material.

Data supplied from the esp@cenet database - Worldwide